

19. NORMATIV HUJJATLAR.

1. GOST 21.101-97. Mejdugosudarstvennyy standart. Osnovnyye trebovaniya k proyektnoy i rabochey dokumentasii/sistema dlya stroitelstva – 32 s.

2. Turli materiallar uchun Puasson koeffisiyenti μ va elastiklik moduli E ning qiymatlari.

2.1-jadval

Materiallarning nomi	Puasson koeffisiyenti μ	Elastiklik moduli E (MPa)
Po'lat	0,24 – 0,33	$(2,0-2,1) 10^5$
Mis	0,31 – 0,34	$(0,84-1,3) 10^5$
Bronza	0,32 – 0,35	$(1,05-1,15) 10^5$
Cho'yan	0,23 – 0,27	$(1,15-1,60) 10^5$
Qo'rg'oshin	0,45	$0,17 10^5$
Latun	0,32 – 0,42	$(0,90-1,00) 10^5$
Alyuminiy va dyuralyuminiy	0,32 – 0,36	$(0,59-0,71) 10^5$
Kauchuk	0,47	$0,00008 10^5$
Shisha	0,25	$0,56 10^5$
Yog'och: tola bo'yicha	-	$(0,10-0,12) 10^5$
yo'nalishda tolaga tik	-	$(0,005-0,01) 10^5$
yo'nalishda		

3. Ruxsat etilgan normal kuchlanishlarning qiymatlari.

2.2-jadval

Materiallarning nomi	$[\sigma_y]$ (MPa)	$[\sigma_c]$ (MPa)
Cho'yan	28 – 80	120 – 150
Po'lat st.1	120	120
st.2	140	140
st.3	160	160
Mis	30 – 120	30 - 120
Latun	70 – 140	70 – 140
Bronza	60 – 120	60 – 120
Alyuminiy	30 – 80	30 – 80
Duralyuminiy	80 – 150	80 – 150
Qarag'ay (tolalar bo'yicha)	7 – 10	10 – 12
Dub (tolalar bo'yicha)	9 – 13	13 – 15
Tosh (kladka)	0 , 3	0,4 – 4,0
G'isht (kladka)	0 , 2	0,6 – 2,5
Beton	0,1 – 0,7	1,0 – 9,0